

CALCOT

LIMESTONE • TUMBLED

The sister stone to our best-selling Neranjo limestone with some extra character and fossils. This stone could easily be mistaken for an English limestone.



FORMAT (CM)

60 x Random x 1.5

AVAILABILITY

Usually in stock

Suitable for interior walls, sealing required.



TECHNICAL DATA

Petrographic Description

A chemicular nodular lithotype this is particularly heterogenous due to the presence of different microtextures. In places there are microtextures of dentritic or feather micrite up to 3-4mm in size with a varying degree of branching surrounded by spatic calcite as well as dominions composed of micrite of bacterial origin in spartic crystals whilst intense concentrations of ostracods can be observed in places.

TEST	STANDARD	RESULT
Apparent Density	BS EN 1936 : 2006	2628.8kg/m ³
Open Porosity	BS EN 1936 : 2006	3.3%
Water Absorption at Atmospheric Pressure	BS EN 13755 : 2008	0.85%
Flexural Strength (3 Point)	BS EN 12372 : 2006	11.4MPa
Frost Resistance (56 Cycles)	BS EN 12371 : 2010	10.61MPa
Abrasion Resistance	BS EN 14157 : 2004	21.0mm
Thermal Shock Resistance	BS EN 14066 : 2013	-0.24%
Slip Resistance (Dry)	BS EN 14231 : 2003	PTV 64
Slip Resistance (Wet)	BS EN 14231 : 2003	PTV 38

- ✓ Suitable for use with underfloor heating
- ✓ Suitable for use in wet areas

For any further information or advice, please contact our team.

INSTALLATION, CARE & MAINTENANCE ADVICE

Please refer to the installation guides on our website.