

OLD WESTMINSTER

SANDSTONE • WORN & PATINATED

High-quality reclaimed York sandstone is expensive and hard to find. Take a long, hard look at these flagstones. Can you believe it's not genuine, reclaimed York stone?



FORMAT (CM)

60 x Random x 2.2

AVAILABILITY

Usually in stock

Suitable for interior floors, sealing required.



TECHNICAL DATA

TEST	STANDARD	RESULT
Bulk Density	BS EN 1936 : 2006	2695kg/m ³
Open Porosity	BS EN 1936 : 2006	0.2%
Water Absorption at Atmospheric Pressure	BS EN 12372 : 2006	2.8%
Flexural Strength (3 Point)	BS EN 12372 : 2006	30.1MPa
Frost Resistance (56 Cycles)	BS EN 12371 : 2010	3MPa
Abrasion Resistance	BS EN 14157 : 2004	20.5mm
Slip Resistance (Dry)	BS EN 14231 : 2003	PTV 34.3
Slip Resistance (Wet)	BS EN 14231 : 2003	PTV 19.5

✓ Suitable for use with underfloor heating

For any further information or advice, please contact our team.

INSTALLATION, CARE & MAINTENANCE ADVICE

Please note that this product will have some thickness variation as a result of the riven process used to create the surface. When installing it is important to always use a substantial adhesive/mortar bed. Please refer to the installation guides on our website.