


OLD WESTMINSTER

SANDSTONE - WORN

Previously known as Old London

Good quality reclaimed sandstone is hard to find and expensive. It is not just the intrinsic quality of this stone that makes it such a good match, but the way that stones from different beds are mixed to mimic the varied tones and textures of old slabs, and the colour-enhancing coating that is applied.



FORMAT (CM)

60 x Random x 2.2

AVAILABILITY

Usually in stock

NOTES

Suitable for interiors floors, sealing with Stone Shield required.

TECHNICAL DATA

TEST	STANDARD	RESULT
Bulk Density	BS EN 1936 : 2006	2695kg/m ³
Open Porosity	BS EN 1936 : 2006	0.2%
Water Absorption at Atmospheric Pressure	BS EN 12372 : 2006	2.8%
Flexural Strength (3 Point)	BS EN 12372 : 2006	30.1MPa
Frost Resistance (56 Cycles)	BS EN 12371 : 2010	3MPa
Abrasion Resistance	BS EN 14157 : 2004	20.5mm
Slip Resistance (Dry)	BS EN 14231 : 2003	PTV 34.3
Slip Resistance (Wet)	BS EN 14231 : 2003	PTV 19.5

✓ Suitable for use with underfloor heating

For any further information or advice, please contact our team.

INSTALLATION, CARE & MAINTENANCE ADVICE

Please note that this product will have some thickness variation as a result of the riven process used to create the surface. When installing it is important to always use a substantial adhesive/mortar bed. Please note that due to the nature of the material, this stone should be sealed with Stone Shield only and not with our standard sealers. Please refer to the installation guides on our website.

CA' PIETRA

UK
CA

CAPIETRA.COM